



Hysol MB 50

High performance soluble metalworking fluid

Description

Castrol Hysol™ MB 50 is a high performance soluble metalworking fluid formulated without formaldehyde releasing agents. It contains an additive package that may help to enhance machining performance and surface finish. It also provides excellent product stability which helps to lower the overall operational costs.

Hysol MB 50 is suitable for large central systems and single sump machines.

Application

Hysol MB 50 is especially designed for machining of ferrous and aluminium alloys.

ü ü suggested core application ü possible application; please consult Castrol representative prior to use

	Cast Iron	Low-medium alloyed steel	High alloyed - stainless steel	Aluminium alloys	Titanium alloys	Magnesium alloys	Yellow metals
Grinding	ü	ü ü	ü ü	ü ü			ü
Milling, Turning (general machining)	ü ü	ü ü	ü ü	ü ü	ü ü		ü
Drilling	ü ü	ü ü	ü ü	ü ü	ü		ü
Reaming, Tapping	ü ü	ü ü	ü	ü ü			ü
Broaching	ü ü	ü		ü			ü

Advantages

- Extended fluid life can help to reduce maintenance and downtime
- Low foam in recommended water conditions (see details below)
- Lubrication package designed to try to help enhance tool life and improve surface finish on aluminium, titanium and ferrous machining
- Good wetting properties can help to reduce coolant drag out and help deliver cleaner machine tools and components
- Suitable for a wide range of materials and applications provides opportunity for product consolidation
- Formulated without formaldehyde releasing agents which help you to fulfil aspects of legislative requirements and waste treatment requirements that specify that these chemicals are excluded

Typical Characteristics

	Test Method	Unit	Value
<u>Concentrate</u>			
Appearance	Visual		Amber
Mineral oil content	Calculated	Wt%	50
<u>Emulsion</u>			
Appearance	Visual		Milky
pH (5%)	DIN 51369 ASTM E70-97		9.7
Refractometer Factor			1.0

Subject to usual manufacturing tolerances.

Recommended Concentrations

Grinding	5-7%
General Machining	5-8%
Drilling	6-8%
Reaming and tapping	7-10%
Broaching	8-10%
Water range	100-1000 ppm CaCO ₃

Storage

To avoid product deterioration always keep the container/drum tightly sealed. Store the product in a cool, dry place away from direct sunlight. Prevent exposure to frost and avoid water ingress. For optimum product stability, it is preferable to store the product indoors between 5°C and 45 °C / 41°F and 113°F.

For more details, please refer to the product safety data sheet.

Hysol MB 50
07 Jan 2021
Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, Technology Centre , Whitchurch Hill , Pangbourne , Reading , RG8 7QR , United Kingdom
<http://msdspds.castrol.com>